AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Hurford Wholesale

400 Stapylton-Jacobs Well Road

Stapylton QLD 4207

Test Number : 19-004152

Issue Date

Print Date

26/09/2019 26/09/2019

Sample Description Clients Ref : "French Oak"

Solid hardwood flooring Colour : Natural End Use : Flooring

Nominal Composition: Timber

Nominal Mass per Unit Area/Density: Approx 12.4kg/m2

Nominal Thickness: 21mm

AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 23/07/2019
Date Tested 25/09/2019

CHF Value	1	2	3	Mean	
Length	4.7	4.7	-	-	kW/m²
Width	4.7	5.0	4.2	4.6	kW/m²
HF-30 Value	1	2	3	Mean	
Length	-	-	-	-	kW/m²
Width	-	-	-	-	kW/m²
Smoke Value	1	2	3	Mean	
Length	6	6	-	-	%.min
Width	8	12	5	8	%.min

Blistering

181036 37786 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

- Performance & Approvals Testing

: Accreditation No.

: Accreditation No. 985

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



VIICHAEL A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Hurford Wholesale

400 Stapylton-Jacobs Well Road

Stapylton QLD 4207

Test Number : 19-004152

Issue Date

Print Date : 26/09/2019

26/09/2019

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

181036 37786 Page 2 of 2

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

may be used in advertising providing the content and format of the advertisement have been approved by

- Chemical Testing - Mechanical Testing

- Performance & Approvals Testing

: Accreditation No. : Accreditation No.

: Accreditation No. 985 : Accreditation No. 1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd



MICHAEL A. JACKSON B.Sc.(Hons)

Albert